



MATERIALS FOR 3D PRINTING

INCONEL



**DANISH
TECHNOLOGICAL
INSTITUTE**

Inconel 625

Nickel alloy

The material properties for Inconel are high strength, good ductility, and good resistance to corrosion. Inconel is suitable for parts that repeatedly alternate between heat and cold at high loads.

We print Inconel using Laser Powder Bed Fusion technology, which works with powder and uses a laser to weld the powder layers together. This technology requires a support structure to attach the part to the build platform. The support is mechanically removed after printing.

The technology can produce parts that comply with ISO 2768-m 1; however, the tolerances depend significantly on the geometry of the part. At the Danish Technological Institute, our 3D printing production is also ISO 9001 certified.

MATERIAL PROPERTIES

TENSILE STRENGTH [Rm]	905 ±55 MPa
YIELD STRENGTH [Rp0,2]	620 ±30 MPa
ELONGATION AT BREAK [A]	42 ±6 %
VICKERS HARDNESS [HV10]	285 ±15
PART DENSITY	>99,8 %
MATERIAL MASS DENSITY	8,44 g/cm ³

SURFACE TEXTURE

Media blasted

Deburred

Processed

Average roughness [Ra]	8 ±2	3 ±1	0,8
------------------------	------	------	-----

Danish Technological Institute - Industrial 3D-printing

Email: 3dprint@dti.dk

Phone: 7220 1701

www.dti.dk/3dprinting



Technology:

- Laser Powder Bed Fusion

Printer:

- SLM Solutions - SLM280

Build volume:

- 280 x 280 x 365 mm

Application:

- Industrial use

Possible post-processing:

- De-stressing
- Heat treatment
- Deburring
- Media blasting
- Conventional processing

Customization:

Contact us if you have specific requests for surface roughness and material properties.

Design features:

- Minimum feature size 0,6 mm
- Minimum channel size Ø2 mm
- Minimum wall thickness 1 mm
- Support for overhangs less than 45°
- Hole for emptying powder Ø5 mm

Examples of use

- Turbine blades for aviation and aerospace.
- Pumps and valves for the oil and gas industry.
- Implants and surgical solutions



**DANISH
TECHNOLOGICAL
INSTITUTE**

Visit our
website to
see our AM
services